



U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE (REV. 10-95)		ATTORNEY'S DOCKET NUMBER CM2207MQL
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371		U.S. APPLICATION NO. (if known, see 37 CFR 1.5) 10/089343
INTERNATIONAL APPLICATION NO. PCT/US00/27137	INTERNATIONAL FILING DATE 02 October 2000	PRIORITY DATE CLAIMED 08 October 1999
TITLE OF INVENTION Adhesives Comprising Linear, Isotactic Polymers		
APPLICANT(S) FOR DO/EO/US DYATLOV, Valery Alexandrovich et al.		
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information.		
<ol style="list-style-type: none"> <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. <input type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(l). <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date. <input checked="" type="checkbox"/> A copy of the International Application was filed (35 U.S.C. 371(c)(2)) <ol style="list-style-type: none"> <input type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau). <input type="checkbox"/> has been transmitted by the International Bureau. <input checked="" type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). <input type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)). <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) <ol style="list-style-type: none"> <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau). <input type="checkbox"/> have been transmitted by the International Bureau. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. <input checked="" type="checkbox"/> have not been made and will not be made. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)). <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)). 		
Items 11. to 16. below concern document(s) or information included:		
<ol style="list-style-type: none"> <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. <input checked="" type="checkbox"/> A FIRST preliminary amendment. <ol style="list-style-type: none"> <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. <input type="checkbox"/> A substitute specification. <input checked="" type="checkbox"/> A change of power of attorney and/or address letter. <input type="checkbox"/> Other items or information: <i>EL 483621522715</i> 		
<small>"Express Mail" mailing label number Date of Deposit</small>		
<small>I hereby certify that this paper/fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to The Assistant Commissioner of Patents, Washington, D.C. 20231.</small>		
<small>Administrator Mailing Application Signature</small> 		

U.S. APPLICATION NO. (if known, see 37 CFR 1.5) 10/089343		INTERNATIONAL APPLICATION NO. PCT/US00/26911		ATTORNEY'S DOCKET NUMBER CM2202MQL	
				CALCULATIONS PTO USE ONLY	
ENTER APPROPRIATE BASIC FEE AMOUNT = \$740					
Surcharge of \$130.00 for furnishing the oath or declaration later than [] 20 [] 30 months from the earliest claimed priority date (37 CFR 1.492(e)).					
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	7-20 =	0	x \$18.00	\$0	
Independent Claims	2-3 =	0	x \$84.00	\$0	
MULTIPLE DEPENDENT CLAIM(S) (if applicable)			\$280.00	\$0	
TOTAL OF ABOVE CALCULATIONS =			\$740		
Processing fee of \$130.00 for furnishing the English translation later than [] 20 [] 30 months from the earliest claimed priority date (37 CFR 1.492(f)).			\$0		
TOTAL NATIONAL FEE =			\$740		
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28,3.31). \$40.00 per property +			\$0		
TOTAL FEES ENCLOSED =			\$740		
			Amount to be refunded	\$	
			charged	\$	
<p>a. [] A check in the amount of \$ ____ to cover the above fees is enclosed.</p> <p>b. [x] Please charge my Deposit Account No. <u>16-2480</u> in the amount of \$ <u>740</u> to cover the above fees. A duplicate copy of this sheet is enclosed.</p> <p>c. [x] The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>16-2480</u>. A duplicate copy of this sheet is enclosed.</p>					
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.					
SEND ALL CORRESPONDENCE TO:					
A. M. Stone, Patent Attorney Customer Number 27752				 Signature <u>T. David Reed</u> Name <u>32,931</u> Registration Number	

CM2207MQL

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In the U.S. National Phase Entry
Under 35 USC 371 from
DYATLOV, Valery Alexandrovich et al.
Int'l Application No. PCT/US00/27137
Filed in the RO/US on 02 October 2000

Entitled:	Adhesives Comprising Linear, Isotactic Polymers
-----------	----------------------------------------------------

PRELIMINARY AMENDMENT UNDER 37 CFR §1.112

Assistant Commissioner for Patents
Box PCT
Washington, D. C. 20231

Dear Sir:

Prior to Examination and computation of the fees for entering the captioned International Application into the U. S. National Phase, please preliminarily amend the above-identified application as follows and consider the following Remarks.

AMENDMENTS

IN THE CLAIMS

5. A polymeric adhesive according to Claim 1
wherein
said homopolymer is polypropylene.
6. An article comprising according to Claim 1
wherein
said adhesive is deployed as a construction element.

REMARKS

Claims 1, 2, 3, 4 and 7 remain in this application. Claims 5 and 6 have been amended by eliminating multiple dependencies. Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached page is captioned "Version With Markings to Show Changes Made."

The support for these amendments is found in the claims as originally filed. These amendments are being entered to bring the claims into conformance with, *inter alia*, 37 CFR §1.75, no new matter is added.

Respectfully submitted for Applicants,

By 
T. David Reed
Agent for Applicant
Registration No. 32,931

Cincinnati, Ohio
20 March 2002
(513)627-7025/FAX (513)627-6333

"VERSION WITH MARKINGS TO SHOW CHANGES MADE"

CLAIMS

1. An article comprising a first element and a second element being joined to said first element by means of an adhesive characterized in that said adhesive comprises a polyolefinic homopolymer having an isotacticity of less than 60% of [mmmm] pentad concentration.
2. An article according to claim 1 wherein said homopolymer has a molecular weight of at least 100000g/mol.
3. An article according to Claim 1 wherein said adhesive is stretchable.
4. An article according to Claim 2 wherein said adhesive is elastically expandable.
5. A polymeric adhesive according to any of the preceding claims] CLAIM 1
wherein said homopolymer is polypropylene.
6. An article comprising according to any of the preceding claims] CLAIM 1
wherein said adhesive is deployed as a construction element.

7. A method for providing an adhesive coating comprising a step of applying an adhesive coating selected from the group of hot melt, spray, powder melt, extruded bead, liquid, solvent based, pressure sensitive, and combinations thereof
characterized in that
said polymeric material comprises a polyolefinic homopolymer having an isotacticity of less than 60% of [mmmm] pentad concentration.

ADHESIVES COMPRISING LINEAR, ISOTACTIC POLYMERS

FIELD OF THE INVENTION

The present invention relates to adhesives used for example in assembling articles. Specifically, the present invention relates to elastic adhesives.

BACKGROUND

Adhesives and in particular adhesives comprising olefinic polymers are well known in the art and enjoy widespread usage throughout the industry. Typical areas of application of such adhesive include hygienic articles and in particular disposable absorbent articles, packaging materials, automotive parts, and the like.

Adhesives made from commonly used polyolefins such as PP, PE, PS, PIB have a number of useful properties. They are bio-compatible and food compatible, chemically stable, inert, non toxic materials. However, most of them have poor mechanical properties including insufficient strength/tear resistance, insufficient stretchability/elasticity and the like.

Other adhesives, such as PU based adhesives, have also been widely used for example because of their elastic properties. PU adhesives however have the disadvantage that they are polymerized from the very toxic monomer isocyanate and hence can not be used for many application due to their inherent toxicity caused by residual monomer content.

Several approaches have been proposed in the prior art to provide elastic properties to such adhesives. The most commonly used approach is based on

changing the chemical structure of the polymer by introducing hinged joints/moieties into the main chain of the polymer. These side groups or side chains provide more flexibility to the polymeric backbone preventing crystallization of polymer, lowering the glass transition temperature (Tg) and improving the elasticity of the resulting material. Usually, the hinge groups contain heteroatoms providing flexibility such as oxygen, nitrogen or chlorine placed into the main chain or into bulky side groups. Another approach is mastication of the polymer by blending with special plasticizing agents. Both approaches, however, require heteroatoms to be introduced into the molecule or into the bulk of the coating material.

The third approach proposed in the prior art to provide elastic properties to such adhesives, which is more close to the present invention, is to exploit the formation of hetero-phases which reinforce the bulk material by forming a physical net. To do this the block-co-polymerization of two or more different monomers has been used leading to polymeric backbones comprising blocks with different Tg. This results in micro-phase separation in the bulk with formation of reinforcing crystalline domains of one co-polymer linked with each other by flexible chains of the second co-polymer.

In essence, conventional adhesives carry a wide variety of inherent disadvantages including but not being limited to insufficient strength/tear resistance, insufficient stretchability/elasticity, not being bio-compatible, not being food compatible, comprising heteroatoms such as chlorine and hence leading to toxic residues when burnt, and the like.

It is an object of the present invention to provide adhesives which overcome the disadvantages of the prior art adhesives.

It is an further object of the present invention to provide articles which comprise elastic adhesives.

It is an further object of the present invention to provide a method for manufacturing adhesive of the present invention.

SUMMARY OF THE INVENTION

The present invention provides an article comprising a first element and a second element being joined to said first element by means of an adhesive. The article is characterized in that said adhesive comprises said adhesive comprises a polyolefinic homopolymer having an isotacticity of less than 60% of [mmmm] pentad concentration.

The present invention further provides a method for providing the aforementioned adhesive coating comprising a step of applying an adhesive coating selected from the group of hot melt, spray, powder melt, extruded bead, liquid, solvent based, pressure sensitive, and combinations thereof.

DETAILED DESCRIPTION OF THE INVENTION

The present invention provides an article comprising a first element and a second element being joined to said first element by means of an elastic adhesive comprising a polyolefinic homopolymer.

The term "polyolefinic homopolymer" as used herein refers to those polyolefins which comprise only one phase of molecules all of which exhibiting a similar stereochemical configuration. For example, blends of atactic and isotactic polymers where the two phases have polymerized simultaneously are excluded when this term is used. The term homopolymer includes copolymers where all molecules exhibit a similar stereochemical configuration.

The polyolefinic homopolymer of the present invention may comprise linear isotactic polymers having a structure of one or several C₃ to C₂₀ olefinic monomers, having an isotacticity of less than 60%, preferably less than 50%,

more preferably less than 40%, and most preferably less than 30% of [mmmm] pentad concentration, and having an isotacticity of more 8%, preferably more than 10%, more preferably more than 12%, and most preferably more than 15% of [mmmm] pentad concentration. Preferably, the polyolefinic homopolymer is polypropylene.

The isotacticity of the homopolymers may be reduced compared to the isotactic polypropylenes of the prior art due to a statistic distribution of stereoscopic errors in the polymer chain. The term "stereoscopic error" refers to a stereoscopic sequence characterized by a [mrrm] pentad. In this case, the central monomer has a stereo configuration opposed to the other four monomers in this pentad. The [mrrm] pentad concentration of this polymer therefore is above the statistical probability of $p^2 (1-p)^2$ where $p=[m]$ and hence $1-p=[r]$ and $p^4=[mmmm]$. Preferably, the pentad concentration is at least $[p (1-p)]^q p (1-p)$ with q being 0.8, more preferably q being 0.6, yet more preferably q being 0.4, yet more preferably q being 0.2, most preferably q being 0.1.

In some embodiments of the homopolymer and in particular in those embodiments where the crystallinity is reduced by means of single stereo errors, a low content of atactic sequences has proven beneficial to the properties of the adhesive of the present invention. Preferably, the [rmrm] pentad concentration is below 6%, more preferably below 5%, yet more preferably below 4%, yet more preferably below 3%, most preferably below 2.5%.

In some embodiments of the homopolymer and in particular in those embodiments where the crystallinity is reduced by means of single stereo errors, a low content of syndiotactic sequences has proven beneficial to the properties of the adhesive of the present invention. Preferably, the [rrrr] pentad concentration is below 6%, more preferably below 5%, yet more preferably below 4%, yet more preferably below 3%, most preferably below 2.5%.

Alternatively, the homopolymer of the present invention may include sequences of atactic and isotactic blocks of polymer.

Preferably, the mean molecular weight M_w of the polymer is above 100000 g/mol, more preferably above 200000 g/mol, yet more preferably above 250000 g/mol, yet more preferably more than 300000 g/mol, most preferably more than 350000 g/mol. Higher molecular weights are particularly beneficial where elastic and tear resistance properties of the adhesive material desired.

For some applications such as adhesion to polymers and mammalian tissue, it is preferred that the molecular weight is below 200000g/mol, more preferably below 175000g/mol, most preferably below 150000g/mol.

The glass temperature T_g is between -50 and +30 °C. Preferably the glass temperature is below 10°C, more preferably below 5°C, yet more preferably below 0°C, most preferably below -6°C. The melt temperature of the polymer is obtained after heating the sample 150°C and subsequently cooling the polymer to -50°C.

Without wishing to be bound by this theory, the polyolefinic polymers exhibit a semi-crystalline structure. The structure contains elastic amorphous areas of nano-scale-size reinforced with self arranged crystalline domains of nano-crystals. The formation of brittle macro-crystalline material from the polymer is achieved by introducing the defects into the polymeric backbone. Isolated monomer units with opposite stereo configuration have been used as the defects, i.e. single stereo errors.

Suitable polymers and a process for manufacturing such polymers are described in PCT patent application EP99/02379 incorporated herein by reference. A catalyst combination suitable for the preparation of such polymers is described in PCT patent application EP99/02378 incorporated herein by reference. Preferably,

the process of PCT patent application EP99/02378 is carried out by temperatures of less than 30°C, more preferably less than 25°C, yet more preferably less than 20°C, most preferably less than 15°C to increase the molecular weight of the resulting polymer. In order to increase the molecular weight, the polymerization is preferably carried out in liquid monomer such as in liquid propene. If it is desired to increase the molecular weight, the catalyst is preferably used in combination with the boron activators mentioned in PCT patent application EP99/02378.

Other suitable polymers and a process for manufacturing such polymers is described in WO99/20664 incorporated herein by reference.

In the prior art, a wide variety of suitable techniques to provide adhesive coatings are known such as applying an adhesive in a form including but not being limited to hot melt, spray, powder melt, extruded bead, liquid, solvent based, pressure sensitive, meltblown fibers and combinations thereof. The aforementioned methods for providing adhesive coatings all have specific advantages which are known to the skilled person. Hence, the skilled person will be able to select a suitable method for providing an adhesive coating of the present invention depending on the specific requirement of the respective application of the adhesive.

The adhesive of the present invention has been found to be able to adhere to polished surfaces such as metal plates, PTFE coated surfaces, polymeric surfaces and the like. The adhesive of the present invention is also suitable for adhering to mammalian tissue such as epidermal tissue.

Preferably, the adhesion force between the two elements of the article of the present invention is adjusted to be at least 5 Newton per centimeter, more preferably at least 10N/cm, yet more preferably 20N/cm, most preferably 40N/cm. Of course, if lower peel forces are desired the adhesive properties such

as molecular weight can be changed accordingly. Alternatively, the same peel force requirement apply when surfaces are attached to each other. The peel forces are measured with respect to the specific surfaces they are used on.

The adhesive of the present invention has further been found to only release relative small amounts of odor even in the melt state. In particular, it is possible to manufacture the adhesive of the present invention without the use of solvents and hence, in some embodiments of the present invention, the adhesive does contain solvents.

In some embodiments and in particular in those embodiments having a high molecular weight, the adhesive of the present invention has been found to exhibit increased temperature stability compared to prior art adhesives. This is partly due to the fact that for the adhesives of the present invention a homopolymer is used and is partly due to the high molecular weight of the homopolymer. Preferably, the adhesive material of the present invention has a melting point of at least 100°C, more preferably of at least 110°C, more preferably of at least 120°C, most preferably of at least 130°C. The melt temperature of the polymer is obtained after heating the sample 150°C and subsequently cooling the polymer to -50°C. If desired, higher melting point may be achieved by blending the homopolymer for example with conventional isotactic polymer such as polypropylene.

Alternatively and in particular in those embodiments in which the adhesive has a relatively low molecular weight, melting point of around 50°C can be achieved. Such melting point can be used for deactivating the adhesive where this is desired. Heating the adhesive to its melting point will cause the adhesive to flow and hence can be peeled off at very low peel forces.

The adhesive of the present invention has been found to be stretchable as well as elastic. The stretchability of the adhesive versus its elastic behavior can be

adjusted by means of the tacticity of the homopolymer of the present invention. The adhesive material of the present invention has been found to be stretchable without tearing to at least 500% of its original length, more preferably 1000% of its original length, yet more preferably to at least 1500% of its original length, most preferably to at least 2000% of its original length. In addition, the adhesive material of the present invention preferably recovers within 10 minutes after being stretched and held for 1 minute to 500% of its original length back to less than 300% its original length, preferably less than 200% its original length, most preferably less than 150% of its original length. In addition, the adhesive of the present invention has been found to exhibit a low compressive set. The adhesive of the present invention recovers within 10 minutes after a compression to 50% of its original thickness for 1 minute to at least 60% of its original thickness, more preferably at least 70% of its original thickness, yet more preferably to at least 80% of its original thickness, yet more preferably to at least 90% of its original thickness, most preferably to at least 95% of its original thickness. The compressibility of the adhesive of the present invention can be adjusted by increasing the tacticity of the homopolymer or by blending the low tacticity homopolymer with conventional isotactic polymer such as polypropylene.

Without wishing to be bound by this theory, it is believed that the rheological properties of the adhesive of the present invention, i.e. the storage or elastic modulus G' and the viscosity modulus G'' , are indicative of its creep and its peel/quick stick behavior respectively during use. The G' and G'' values at low frequencies (approximately 0.01rad/s to 1rad/s) and at high frequencies (100rad/s to 1000rad/s) are believed to relate to the behavior of the adhesive at application and at removal respectively. It is well known in the art, to measure G' and G'' over a broad range of frequencies, for example a Rheometric Scientific RS-5 rheometer could be used. The measurement of G' and G'' should be carried out at the desired usage temperature, i.e. room temperature of 25°C for most applications or 37°C for body related applications.

Preferably, the adhesive of the present invention has a viscosity modulus $G''(1\text{rad/s})$ of less than 30000 Pa, more preferably less than 25000 Pa, yet more preferably less than 20000 Pa, most preferably less than 15000 Pa. Without wishing to be bound by this theory, it is believed that these values of $G''(1\text{rad/s})$ are indicative of the adhesive not flowing away when the adhesive is applied to the surface.

Preferably, the adhesive of the present invention has a viscosity modulus $G''(1\text{rad/s})$ of at least 500 Pa, more preferably at least 1000 Pa, yet more preferably at least 1500 Pa, most preferably at least 2000 Pa. Without wishing to be bound by this theory, it is believed that these values of $G''(1\text{rad/s})$ are indicative of the adhesive being able to conform to the topology of the surface it is applied to.

Preferably, the adhesive of the present invention has a viscosity modulus $G''(100\text{rad/s})$ of less than 30000 Pa, more preferably less than 20000 Pa, yet more preferably less than 15000 Pa, most preferably less than 10000 Pa. Without wishing to be bound by this theory, it is believed that these values of $G''(100\text{rad/s})$ are indicative of the adhesive not flowing away upon removal from the surface.

Preferably, the adhesive of the present invention has a viscosity modulus $G''(100\text{rad/s})$ of at least 1000 Pa, more preferably at least 2000 Pa, yet more preferably at least 3000 Pa, most preferably at least 4000 Pa. Without wishing to be bound by this theory, it is believed that these values of $G''(100\text{rad/s})$ are indicative of the adhesive not breaking upon removal from the surface.

Preferably, the adhesive of the present invention has a viscosity modulus $G'(1\text{rad/s})$ of less than 30000 Pa, more preferably less than 25000 Pa, yet more preferably less than 20000 Pa, most preferably less than 15000 Pa. Preferably, the adhesive of the present invention has a viscosity modulus $G'(1\text{rad/s})$ of at

least 500 Pa, more preferably at least 1000 Pa, yet more preferably at least 1500 Pa, most preferably at least 2000 Pa. Without wishing to be bound by this theory, it is believed that these values of G'(1rad/s) are indicative of the adhesive maintaining its elastic properties when the adhesive is applied to the surface.

Preferably, the adhesive of the present invention has a viscosity modulus G'(100rad/s) of less than 30000 Pa, more preferably less than 25000 Pa, yet more preferably less than 20000 Pa, most preferably less than 15000 Pa.

Preferably, the adhesive of the present invention has a viscosity modulus G'(100rad/s) of at least 2000 Pa, more preferably at least 3000 Pa, yet more preferably at least 4000 Pa, most preferably at least 5000 Pa. Without wishing to be bound by this theory, it is believed that these values of G'(100rad/s) are indicative of the adhesive maintaining its elastic properties upon removal from the surface.

Preferably, the ratio of G'(1 rad/s) / G"(1 rad/s) is in the range of 1 to 30. This is believed to be indicative of the flow behavior of the adhesive of the present invention during application of the adhesive to the surface of the substrate.

Of course, if other values of G' and G" are desired, the adhesive properties can be adjusted accordingly within the above given limits.

The adhesive according to the present invention may also be used as a construction element in an article. Such articles include but are not limited to toys, furniture, clothing, shoes, sport equipment, complex constructions such as buildings, cars, household appliances, and the like. Having regard to the specific advantages of the polymers used for the articles of the present invention, it will be readily apparent to the skilled practitioner to apply and to optionally modify the adhesives according to the present invention as construction elements in the above and similar articles.

The adhesives of the present invention are suitable for joining non-sealable polyolefinic surfaces, for joining and adhering to wood surfaces, for joining and adhering to Plexiglas surfaces and the like.

The adhesives are suitable for applications where the adhesive needs to be stretchable, i.e. where the bonded surfaces of the first element and the second element should be allowed to make small movements relative to each other. For example, the adhesive of the present invention may be used as a binder resin for nonwoven web materials. The adhesive of the present invention will allow for further processing of such bonded nonwoven web materials such as for example mechanical activation such as by ring rolling.

The adhesives of the present invention may for example be activated by electromagnetic radiation such as infrared, UV or visible radiation, by ultrasonic wave and the like.

Additives such as those known in the art may be added to the adhesive of the present invention. For example, the addition of talc is suitable for modifying the adhesive properties.

CLAIMS

1. An article comprising a first element and a second element being joined to said first element by means of an adhesive characterized in that said adhesive comprises a polyolefinic homopolymer having an isotacticity of less than 60% of [mmmm] pentad concentration.
2. An article according to claim 1 wherein said homopolymer has a molecular weight of at least 100000g/mol.
3. An article according to Claim 1 wherein said adhesive is stretchable.
4. An article according to Claim 2 wherein said adhesive is elastically expandable.
5. A polymeric adhesive according to any of the preceding claims wherein said homopolymer is polypropylene.
6. An article comprising according to any of the preceding claims wherein said adhesive is deployed as a construction element.

7. A method for providing an adhesive coating comprising a step of applying an adhesive coating selected from the group of hot melt, spray, powder melt, extruded bead, liquid, solvent based, pressure sensitive, and combinations thereof
characterized in that
said polymeric material comprises a polyolefinic homopolymer having an isotacticity of less than 60% of [mmmm] pentad concentration.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 10/00, 4/64, C09J 123/16		A1	(11) International Publication Number: WO 96/26967 (43) International Publication Date: 6 September 1996 (06.09.96)
(21) International Application Number: PCT/US96/00737		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KG, KZ, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 19 January 1996 (19.01.96)		Published <i>With international search report.</i>	
(30) Priority Data: 08/396,966 1 March 1995 (01.03.95) US			
(71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).			
(72) Inventors: SIEDLE, Allen, R.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). MILLER, John, A.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). LAMANNA, William, M.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).			
(74) Agents: PETERS, Carolyn, V. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).			

(54) Title: TRIS(PENTAFLUOROPHENYL)BORATE COMPLEXES AND CATALYSTS DERIVED THEREFROM

(57) Abstract

Tris(pentafluorophenyl)borane complexes having the general formula $(C_6F_5)_3Bx(YXH)^q$ wherein X is oxygen, or sulfur; q is 1 to 3; Y is a hydrogen atom, R^1 , $(R^2)_3Si$, or $(R^3)_2C=N^-$; R^1 is a hydrocarbyl group containing 1 to 500 carbon atoms, and may contain a divalent oxygen and further may be a fluorine-containing hydrocarbyl group; R^2 is independently a linear or branched alkyl group containing 1 to 25 carbon atoms, or a phenyl group, further R^2 may contain a SiO^- group; and R^3 is independently a hydrocarbyl group containing 1 to 25 carbon atoms, R^3 may be a hydrogen atom provided both R^3 groups selected are not hydrogen atoms; and to complexes containing the borane complexes with an organometallic compound, either as a neutral compound or as an acidic salt that are useful as catalysts for polymerization and copolymerization of olefins and to polymeric products prepared using these catalysts.

DECLARATION COMBINED WITH POWER OF ATTORNEY

Attorney Docket No. CM2207MQ/VB

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled Adhesives Comprising Linear, Isotactic Polymers the specification of which

(check one) is attached hereto.
 was filed on 02 October 2000 as United States Application No. or
PCT International Application Serial No. PCT/US00/27137 ✓
and was amended on _____

(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37 Code of Federal Regulations §1.56.

I hereby claim foreign priority benefits under Title 35 United States Code §119(a)-(d) or §365(b) of any foreign application(s) for patent or inventor's certificate, or §365(a) of any PCT International application which designated at least one country other than the United States of America, listed below and have also identified below any foreign application for patent or inventor's certificate, or of any PCT international application having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)Priority Claimed

99120170.8

EP

08 October 1999 ✓

Yes	No
<input checked="" type="checkbox"/>	<input type="checkbox"/>

I hereby claim the benefit under Title 35, United States Code §119(e) of any United States provisional application(s) listed below.

Application Serial No.Filing DateApplication Serial No.Filing Date

I hereby claim the benefit under Title 35 United States Code §120 of any United States application(s), or §365(c) of any PCT International application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35 United States Code §112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37 Code of Federal Regulations §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

U.S. Parent Application Number	PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (If applicable)

As named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

<u>Atty Name</u>	<u>Atty Reg Number.</u>	<u>Associate Power of Attorney Attached</u>
Stephen W. Miller	31,984	[] Yes [X] No
T. David Reed	32,931	
Timothy B. Guffey	41,048	
Donald E. Hasse	29,387	
Brian M. Bolam	37,513	

SEND CORRESPONDENCE TO:

T. David Reed, c/o The Procter Gamble Company (513) 627-7025

Name

5299 Spring Grove Avenue Cincinnati Ohio 45217-1087

Street City State

Zip Code

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

1-^{Full} name of sole or first joint inventor DYATLOV, Valery Alexandrovich

Inventor's signature Valeriy Valeriy Alexandrovich Date 12.01.2001

Residence maly Levshinsky per 12-6, 119034 Moscow, RU

Citizenship RU

Post Office Address maly Levshinsky per 12-6, 119034 Moscow, RU

2-^{Full} name of second joint inventor, if any HANKE, Bernhard

Inventor's signature Bernhard Hanke Date 28.11.2000

Residence Breslauer Str. 12, 65307 Bad Schwalbach, DE

Citizenship DE

Post Office Address Breslauer Str. 12, 65307 Bad Schwalbach, DE

3-^{Full} name of third joint inventor, if any RIEGER, Bernhard

Inventor's signature Bernhard Rieger Date 29.11.2000

Residence Johann-Stockar-Weg 8, 89075 Ulm, DE

Citizenship DE

Post Office Address Johann-Stockar-Weg 8, 89075 Ulm, DE

4-^{Full} name of fourth joint inventor, if any PREUSCHEN, Judith

Inventor's signature Judith Preuschens Date 22.10.10.01

Residence Alfred-Doeblin Str. 37, 55129 Mainz, DE

Citizenship DE

Post Office Address Alfred-Doeblin Str. 37, 55129 Mainz, DE

5-^{Full} name of fifth joint inventor, if any ORROTH, Mike

Inventor's signature Mike Orroth Date 29.10.10.01

Residence Flat 3, 122 Richmond Hill, Richmond, Surrey TW10 6RJ, GB

Citizenship US

Post Office Address Flat 3, 122 Richmond Hill, Richmond, Surrey TW10 6RJ, GB

(Decl.doc)

REVISED 12/97

PO(Same as Residence) 12/99

CM2207MQL

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In the U.S. National Phase Entry
Under 35 USC 371 from
DYATLOV, Valery Alexandrovich et al.
Int'l Application No. PCT/US00/27137
Filed in the RO/US on 02 October 2000

Entitled:	Adhesives Comprising Linear, Isotactic Polymers
-----------	----------------------------------------------------

ASSOCIATE POWER OF ATTORNEY

Assistant Commissioner for Patents
Box PCT
Washington, D.C. 20231


Dear Sir:

You are requested to recognize L. W. Lewis (Registration No. 30,769), P. D. Meyer (Registration No. P-47,792), L. L. Huston (Registration No. 32,994), A. M. Stone (Registration No. 41,335), and P. M. Ulrich (Registration No. 46,404) of The Procter & Gamble Company, Cincinnati, Ohio, and all other attorneys/agents associated with the customer number(s) listed below as Associate Attorneys to prosecute this application, to make alterations and amendments therein, and to transact all business in the Patent Office connected with the application or with the patent granted thereupon.

Please address all future communications to:

A. M. Stone, Patent Attorney
Customer No. 27752

Respectfully submitted for Applicants,

By 
T. David Reed
Agent for Applicant
Registration No. 32,931

Cincinnati, Ohio
20 March 2002
(513) 627-7025/FAX 627-6333